



Avoid A Water Crisis.

CuraPoxy[®] LS Data Sheet

DESCRIPTION

CuraPoxy LS is a solvent free, 100% solids, epoxy coating designed for lining long lengths of potable water pipes. Formulated for broad range corrosion protection, CuraPoxy LS is certified safe in immediate return to service applications for both cold and hot potable water (ANSI/NSF Std. 61) at a maximum film thickness of 40 mils

TYPICAL PIPE LINING USES

- Water distribution lines 1/2" and larger
- Water treatment and storage facilities

COLOR

Blue is the standard product color.

SOLIDS BY VOLUME & VOCs

100% solids by volume.

Volatile Organic Compounds: 0.0 lbs. /gallon

FILM THICKNESS

CuraPoxy LS is a 100% solids epoxy with zero shrinkage. Wet film thickness and final dry film thickness are the same (i.e. 10 mils WFT = 10 mils DFT).

THEORETICAL COVERAGE

160 square feet per gallon at 10 mils thickness. Actual surface coverage will depend on surface irregularities and desired result. Trials are recommended to determine the actual coverage required to yield a desired film thickness for each individual type of installation.

APPLICATION METHOD

CuraPoxy LS is mixed and applied automatically in a 3 to 1 ratio by volume using the CuraFlo Engineered Flow Lining System[®].

THINNING

Do not thin with solvents: Pinholing and loss of adhesion can result. The CuraFlo Engineered Flow Lining System equipment heats the product to obtain the correct viscosity.

CLEAN UP

To clean tools, use acetone, MEK or xylene. To clean skin, wash immediately and thoroughly with soap and water – refer to the Material Safety Data for additional information on health and safety.

POT LIFE

45 minutes for 1 gallon at 72°F. The working life varies depending on the amount and temperature of epoxy mixed and the ambient temperature.

FLUSH REQUIREMENTS

After the curing of CuraPoxy LS, a 15 minute water flush at 2.5 to 3.5 gallons per minute at the highest possible service temperature (180°F for commercial hot, 140°F for domestic hot or 73°F for cold water) is required before returning the pipe to service

SURFACE TEMPERATURE

Minimum recommended: 50°F

Maximum recommended: 120°F

CERTIFICATIONS

ANSI/NSF Standard 61: CuraPoxy LS is certified to the requirements of ANSI/NSF Standard 61 - Drinking Water System Components.

AWWA: CuraPoxy LS meets the physical and performance requirements of ANSI/AWWA C210-92, "Liquid-Epoxy Coating Systems for the Interior and Exterior of Steel Water Pipelines".

IAPMO: CuraPoxy LS is certified to the requirements of IAPMO IGC 189 for application in pressurized metallic water piping systems.

SURFACE PREPARATION

Surfaces to receive coating must be cleaned of all oil, grease, rust, scale, deposits and other contaminants. Contact CuraFlo for specific recommendations.

COMPONENTS AND MIXING

CuraPoxy LS is mixed and applied automatically in a 3 to 1 ratio by volume using the CuraFlo Engineered Lining System.

When mixing by hand, mix only full kits, individually mix both Part A and Part B containers prior to metering 3 parts of Part A to 1 part of Part B by volume into a clean container. Completely mix combined components for a minimum of one minute before transferring contents to a clean container. Continue mixing in the clean container a minimum of one minute before application. Be certain to scrape the sides frequently to attain a thorough mix. Containers need to be mixed prior to metering if contents have settled.

SHELF LIFE AND STORAGE

Shelf Life: 1 year in sealed, unmixed containers at room temperature. Store in sheltered area between 60°F and 80°F (15°C and 27°C). Containers will need to be mixed if contents have settled.

VISCOSITY

Part A; 12,000 to 25,000 cps, Brookfield RVF

Part B; 15,000 to 35,000 cps, Brookfield RVF

SAFETY

Consult the Material Safety Data Sheet for this product concerning health and safety information before using. Strictly follow all notices on the Material

Safety Data Sheet and container label. If you do not fully understand the notices and procedures provided, or if you cannot strictly comply with them, do not use this product. Actual safety measures are dependent on application methods and work environment. Contact CuraFlo to obtain a copy of the Material Safety Data Sheet at 888-428-7235.

PERFORMANCE TESTING

DESCRIPTION	METHOD	RESULT
Tensile Strength	ASTM D 638	7,700 psi
Tensile Ultimate Elongation	ASTM D 638	1.2%
Compressive Strength	ASTM D 695	16,600 psi
Flexural Strength	ASTM D 790	10,600 psi
Hardness, Shore D	ASTM D 2240	88
Adhesion	ASTM D 4541, Steel (SSPC SP-10) Concrete	>2,500 psi Substrate Failure
Temperature Resistance	Steel, Unprimed and Concrete	200° F

Warranty and Disclaimer: CuraFlo warrants its products to be free of manufacturing defects and that they will meet CuraFlo's current published physical properties when applied in accordance with CuraFlo's directions and tested in accordance with ASTM and CuraFlo standards. If within one (1) year from purchase, any product does not meet the physical properties or is defective in manufacture, CuraFlo, at its sole option will either replace the defective product or refund the purchase price. This warranty is void if the product is used contrary to CuraFlo's written directions.

THE AFORESAID IS THE EXCLUSIVE WARRANTY AND IS IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED. THERE IS NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE. UNDER NO CIRCUMSTANCES SHALL CURAFLO BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES OR FOR LOST PROFITS. NO ACTION AGAINST CURAFLO MAY BE COMMENCED MORE THAN ONE (1) YEAR AFTER THE CLAIM ARISES.

To Contact CuraFlo:

Call 888-4-CURAFLO or visit www.curaflo.com

CuraPoxy®LS Data Sheet

CFPD0801025©2008 CuraFlo Franchising